

[54] POLYMER COMPOSITION CONTAINING A
PHYSIOLOGICALLY ACTIVE SUBSTANCE[75] Inventors: Isao Kaetsu; Masaru Yoshida;
Masaharu Asano, all of Takasaki,
Japan[73] Assignee: Japan Atomic Energy Research
Institute, Tokyo, Japan

[21] Appl. No.: 120,896

[22] Filed: Feb. 12, 1980

[30] Foreign Application Priority Data

Feb. 19, 1979 [JP] Japan 54-017298

[51] Int. Cl.³ C08F 2/48; A61K 31/74;
A61K 31/78[52] U.S. Cl. 204/159.22; 424/78;
424/81; 260/37 R[58] Field of Search 204/159.22, 159.23;
424/78, 81

[56]

References Cited

U.S. PATENT DOCUMENTS

3,577,512 5/1971 Shepherd et al. 424/81
3,767,790 10/1973 Gutttag 424/81
4,025,391 5/1977 Kawashima et al. 204/159.22
4,269,821 5/1981 Kreuter et al. 424/81

Primary Examiner—Melvyn I. Marquis

Assistant Examiner—A. H. Koeckert

Attorney, Agent, or Firm—Posnack, Roberts, Cohen &
Spieccens

[57]

ABSTRACT

A polymer composition containing a physiologically active substance and being capable of releasing it at a controlled rate can be prepared by contacting 10 parts, by weight, of one or more polymerizable monomers and 0.1 to 30 parts, by weight, of one or more physiologically active substances and irradiating them with light or an ionizing radiation while maintaining the system in an anhydrous condition and in airless state.

5 Claims, No Drawings